

LITHI-TEK®4500

Technical Data Sheet

Precautions

Avoid contact with skin, eyes and clothing. No respirator is needed when applying this product. Wash hands after use and do not take internally. Please refer to the product Material Data Safety Sheet (MSDS) before using.

Preparation

The preparation process should be followed to ensure adequate penetration and optimum performance. The concrete substrate must be structurally sound, thoroughly dry and clean. Remove all paints, sealers and/or adhesives before application. The substrate must be clean of oil, grease, dirt, wax, curing compounds, efflorescence and other contaminants that might interfere with the penetration of the sealer. If acid is used to clean the concrete, neutralize the surface completely and rinse it with water prior to application. New concrete must be cured at least 28 days.

Application

Test the sealer in an inconspicuous area to ensure the desired coverage and appearance is achieved. Make sure the entire surface is completely dry and free of dust, dirt and debris. Cover all surrounding areas not intended to be coated. Stir the material before using. Apply with a low pressure, high volume pump sprayer, brush or roller. Apply until the surface is saturated but not to the point of puddling. Do not over-apply. If overspray occurs it should be cleaned and removed immediately after sealing. Apply one coat to ensure complete coverage. Please note: Lithi-Tek® 4500 is a concentrated solution that needs to be reconstituted with water prior to application. 1 part water to 1 part Lithi-Tek® 4500. Roll or broom out any puddles until the sealer penetrates into the substrate.